

CONIPUR 380

Catalysed MDI Based PUR Binder

Product description

CONIPUR 380 is single component, solvent free, unpigmented, moisture curing, slightly catalysed binder of medium viscosity based on MDI.

Fields of application

CONIPUR 380 is used as a binder for the manufacturing of rubber granule mats (cylinder production) and rubber mouldings (e.g. for children's playgrounds) by cold-pressing.

Not only rubber granules and rubber buffing can be used but also other elastic materials, such as cork and polyurethane foam can be used.

Properties

Mouldings made from CONIPUR 380 exhibit high mechanical properties.

Due to the solvent and plasticizer free formulation, a binder initiated shrinkage can be excluded.

Technical Data

Density	DIN 51757, at 23 °C	g/cm ³	1.06
Viscosity	at 23 °C	mPas	approx. 3000
NCO content	DIN 53185	%	10.3
Flash point	DIN 51755	°C	> 100
Above figures are guide values and must not be used as a base for specifications!			

Application method

CONIPUR 380 is a single component binder. For use the temperature of the binder should be between 15 and 25 °C. The elastic granules or fibres are mixed with the necessary amount of binder using a suitable mixer.

The amount of binder depends very much on the type and size of the elastic particles to be bound, on compaction and on the application purpose of mouldings or mats. It varies normally from 4 to 20 % by weight.

The duration of mixing depends on the mixer type, but must be at least 2-5 minutes.

The mixture of binder and granules is filled in moulds, compacted and cured until a de-moulding is possible.

The de-moulding time depends very much on the amount of available water, temperature and the presence of catalysts.

A small amount of water can also be added directly to the granules prior to mixing with the binder. The curing process can be shortened significantly by an increase of temperature, which is especially important in mouldings. Fast curing can be achieved when exposed to water vapour.

Pack size

CONIPUR 380 is delivered in 25kg jerry cans, 220 kg drums or in 1'050 kg IBC's.

Colour

dark brown

Storage

Store in original closed packing under dry conditions at a temperature range of 5 - 25 °C.

Do not expose to direct sunlight.

Before use, please see "best before" date on the pail / drum.

Safety precautions

CONIPUR 380 is non-hazardous in its cured condition.

For protective measures, transport regulations and waste management please refer to the Material Safety Data Sheet of the product.

CONIPUR 380 meets the requirements of the EC directive 2004/42/EC.

Industriestr. 26 8207 Schaffhausen Switzerland Tel.: +41 52 644 3600 Fax: +41 52 644 3699 info@conica.com www.conica.com

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the professional competence involved in the application of the product are beyond our control.

As all CONICA guidelines maybe updated as needed, it is user's responsibility to obtain the most recent issue. Registered users can obtain the actual data sheets from our webpage. Hard copies are available upon request.